

BF GOODRICH*Certificate of Analysis*

Send To: ULTRA TUFF 2065 E MAIN ST SUITE C MONTROSE, CO 81401	Ship To: ULTRA TUFF 2065 E MAIN ST SUITE C MONTROSE, CO 81401
W/Ship: QUALITY CONTROL MANAGER	

Scale 5 – No permanent effect 0 – Severe effect

PROPERTIES

Solids	53% (ww) and 45%
pH	9
Viscosity	100-110 KU
Density	1.06 – 1.1

RESISTANCE
(After recovery)

Fuel	4
Diesel	4
Oils	Hydraulic 5
	20W50 5
	Skydrol 0
	Used 5
Acids	Sulfuric 5
(10% solution)	Acetic 5
Alkaline	Sod Hyd 5
	Detergent
Anti-Freeze	Motor 3
	Window 2
Various	Water 5
	Ethanol 5
	190 Proof alcohol 5
	Amonia 5
	Vinegar 5

WEARING DATA

18,000 passes	95%
36,000 passes	88%
54,000 passes	83%
72,000 passes	69%

Wearing results are based on gloss loss at 60 degrees as a percentage of 100

MAR-SCUFF RESISTANCE
(Wt in grams)

One Day	9080
Seven days	9080

Mar-Scuff tests are based on a BYK-Gardner Mar Tester with plastic stylus. Maximum value 9080 gm.